

ROVALMA

THE STEEL INNOVATOR



FECRONI[®]-1800

Remelted Stainless Steel with Enhanced
Corrosion Resistance and Optimal Combination
of Wear Resistance and Toughness

FECRONI[®]-1800

Fecroni[®]-1800 is a remelted martensitic stainless steel specially designed for plastic injection dies. It combines high corrosion resistance and toughness with a high level of polishability and good thermal conductivity. The typical usage hardness range is between 48 to 56 HRc, depending on the specific application. Starting with a careful selection of raw material, continuing with a controlled melting in an electric arc furnace, followed by a special re-melting step and advanced thermo-mechanical treatments, a very clean and fine microstructure is achieved. Furthermore, the dimensional change of Fecroni[®]-1800 during heat treatment is exceptionally low.

Applications

Fecroni[®]-1800 is mainly used in dies for the injection of corrosive thermoplastics or thermosets requiring high levels of polishability. It has also provided very good results when employed in cases of thin walls and critical zones where the toughness of the martensitic stainless steels should be increased. It has further showed beneficial in applications requiring maximum dimensional stability throughout the heat treatment process. Fecroni[®]-1800 has also been particularly successfully used in inserts for high durability dies in order to prevent re-polishing operations and to minimize problems in cooling areas. Finally, it has showed very advantageous in other engineering applications, where the above mentioned combination of properties is required from the tool like: tools for high-speed machines, numerical control or EDM; milling blades for corrosive products; all types of knives for the food industry.

Physical and Mechanical Properties

| Properties | 300 K | 473 K | Unit |
|-----------------------|-------|-------|-------------------|
| Density | 7.78 | 7.73 | g/cm ³ |
| Mechanical Resistance | 1790 | 1682 | MPa |
| Yield Strength 0,2 % | 1520 | 1400 | MPa |
| Elastic Modulus | 210 | | GPa |

The values given in the tables are typical values (neither maximum nor minimum values), for properly heat treated materials at a hardness level of 50-52 HRc.

Thermal Properties

| Properties | 300 K | 473 K | Unit |
|--------------------------------------|-------|-------|----------------------|
| Linear Thermal Expansion Coefficient | - | 11 | x10 ⁻⁶ /K |
| Thermal Diffusivity | 6.3 | 6.1 | mm ² /s |
| Thermal Conductivity | 24 | 24 | W/m·K |
| Specific Heat Capacity | 0.48 | 0.51 | J/g·K |

The values given in the tables are typical values (neither maximum nor minimum values), for properly heat treated materials at a hardness level of 50-52 HRc. Thermal conductivity values are calculated on the basis of thermal diffusivity values measured by laser flash

Designer & Provider of First-Class Tool Materials

ROVALMA, S.A. provides innovation in tool materials. Thanks to comprehensive research, innovative design and development, most recent production techniques as well as in depth quality control, we have achieved significant advances in the knowledge about material forming processes and generated important know-how regarding the production and optimal usage of our materials for a specific application. As a result, we can provide you with **first-class tool steels** for cold and hot work material forming processes and outstanding technical assistance.

We are proud to make our High Performance Tool Steels available to you for your specific applications. Do not hesitate to contact us for the latest information.

Application Engineering Service

In order to fully exploit the advantages and the potentials of ROVALMA's High Performance Tool Steels, we offer our customers the support of our Application Engineering Service. Our highly qualified and dedicated engineers can assist you in selecting the optimized grade for your application and provide you with the corresponding technical recommendations. It is our mission to increase the competitive-advantage of our customers and support them in achieving the highest possible cost-effectiveness.

You can access our service directly by sending an email to: ae-fast@rovalma.com.



ROVALMA, S.A. carries out ongoing research for many applications regarding the usage of the materials here presented. This research often brings along significant advances in the knowledge of a given process and thus important information regarding the best possible usage of the materials for a specific application. We strongly recommend to get in contact with ROVALMA, S.A. for the latest information regarding a specific application.

Rovalma S.A.
HT
C/ Apol·lo, 51
08228 Terrassa (Barcelona)
SPAIN
Tel. (+34) 935 862 949
Fax (+34) 935 881 860

Rovalma S.A.
Head Office
C/ Collita, 1-3
08191 Rubí (Barcelona)
SPAIN
Tel. (+34) 935 862 949
Fax (+34) 935 881 860

Rovalma GmbH
German Office
Geibelstraße 5
12205 Berlin
GERMANY
Tel. +49 (0)30 810 59 717
Fax +49 (0)30 810 59 715

www.rovalma.com

© ROVALMA, S.A. 2021. All rights reserved. This brochure may not be, entirely or partially, reproduced, copied, distributed or modified, without the explicit authorization by ROVALMA, S.A. In particular, it is prohibited to alter the contents and/or use, any information provided herein, out of context. **NOTICE:** All information provided herein is for general information purposes only. The optimal choice of a tool steel depends on many factors, including, but not limited to individual process parameters, allowable tolerances and other production process factors, work conditions and preferences. **DISCLAIMER:** All information provided in this datasheet is provided "AS IS" and "As available" and without warranty, express or implied, of any kind regarding completeness, faultlessness, accuracy, up-to-dateness, individual interpretations, merchantability or fitness for any purpose and no representation contained in this datasheet shall be binding upon ROVALMA, S.A. All information shall be provided and accepted at Reader's / Receiver's risk.